



1501 West 178th Street | Gardena, CA. 90248
310-767-7812 | 800-359-5679 | fax: 310-767-7836
info@matsui-color.com | www.matsui-color.com

WS0472-1 White 301W-10-4

Technical Data Sheet

- **Wet Ink Tack** | Low
- **After Flash Tack** | Low
- **Printability** | Excellent
- **Surface Appearance** | Matte
- **Opacity/Viscosity** |
Excellent/Low
- **Bleed Resistance** | None
- **Flash Temperature** | 160°F
(71°C)/decreases with
deposit thickness
- **Cure Temperature** | 320°F
(160°C)
- **Squeegee Hardness** |
Medium
- **Squeegee Blade** | Sharp
- **Squeegee Angle** | 45 degrees
to screen
- **Squeegee Speed** | Medium
- **Underlay** | Excellent
- **Emulsion** | Direct or indirect
- **Mesh Count** | 86-160 mc in
(34-63 mc cm)
- **Thinner** | RV Additive
- **Thickener** | Thickener B
- **Storage** | 65°F to 95°F (18°C
to 35°C). Avoid direct sun.
- **Cleanup** | Water and mild
soap or detergent
- **Color Range** | White
- **Substrate Type** | Cotton
- **Substrate Color(s)** | Light,
Medium and Dark Fabrics

Description

White 301W-10-4 is a direct print and mixing white for “**Performance**” and high stretch fabrics that can be mixed with “**Neo Pigments**” to achieve an extremely soft hand feel and excellent elasticity.

Features

- Easy to mix and print
- Can be used as a mixing white with Neo Pigments up to 15%
- Excellent printability with no viscosity modifications
- Extremely soft hand feel that PVC inks cannot achieve
- Excellent elasticity, great on Dri-fit performance fabrics
- Creates an opaque white print and superb softness
- OEKO-TEX® Standard 100 certified, CPSIA and HR4040 Compliant
- Is “**PVC Free**” and environmentally safe

Application

Print through fine screen mesh up to 160 mc in (63 mc cm) when cured at 320°F (160°C), **White 301W-10-4** produces the softest prints achievable in textile screen printing today.

Special Recommendations

White 301W-10-4 should be mixed in clean vessels using clean mixing blades and utensils. Any contamination from other ink sources or non-approved additives could make **White 301W-10-4** test positive for restricted PVC's.

- **White 301W-10-4** can be dry cleaned or ironed
- Use Retarder MG 1-5% to help with open time in the screen
- Use Fixer WF-N 1-5% to help with wash fastness
- Use Softener MG 1-4% to help penetrate in to the garment
- Use Thickener B .25-1% to help thicken the ink
- Use RV Additive 1-3% to reduce viscosity